



THE UNITED STATES OF AMERICA

TO ALL TO WHOM THESE PRESENTS SHALL COME:

UNITED STATES DEPARTMENT OF COMMERCE

United States Patent and Trademark Office

December 03, 2004


THIS IS TO CERTIFY THAT ANNEXED HERETO IS A TRUE COPY FROM THE RECORDS OF THE UNITED STATES PATENT AND TRADEMARK OFFICE OF THOSE PAPERS OF THE BELOW IDENTIFIED PATENT APPLICATION THAT MET THE REQUIREMENTS TO BE GRANTED A FILING DATE.

APPLICATION NUMBER: 60/517,128

FILING DATE: November 04, 2003

RELATED PCT APPLICATION NUMBER: PCT/US04/37076

Certified by



Jon W Dudas

Acting Under Secretary of Commerce
for Intellectual Property
and Acting Director of the U.S.
Patent and Trademark Office



BEST AVAILABLE COPY

Please type a plus sign (+) inside this box

+

PTO/SB/16 (5-03)

Approved for use through 4/30/2003. OMB 0651-0032

U.S. Patent and Trademark Office; U.S. DEPARTMENT OF COMMERCE

Under the Paperwork Reduction Act of 1995, no persons are required to respond to a collection of information unless it displays a valid OMB control number.

PROVISIONAL APPLICATION FOR PATENT COVER SHEET

This is a request for filing a PROVISIONAL APPLICATION FOR PATENT under 37 CFR 1.53(c).

INVENTOR(S)					
Given Name (first and middle (if any))	Family Name or Surname	Residence (City and either State or Foreign Country)			
Frank	Ko	Philadelphia, PA			
Sachiko	Sukigara	Philadelphia, PA			
Milind	Ghandi	Philadelphia, PA			
Jonathan	Ausyete	Philadelphia, PA			
<input type="checkbox"/> Additional inventors are being named on the _____ separately numbered sheets attached hereto					
TITLE OF THE INVENTION (280 characters max)					
Electrospun Carbon Nanotube Reinforced Silk Fibers					
Direct all correspondence to: CORRESPONDENCE ADDRESS					
<input checked="" type="checkbox"/> Customer Number		26259		Place Customer Number Bar Code Label here	
OR Type Customer Number here					
<input checked="" type="checkbox"/> Firm or Individual Name		Kathleen A. Tyrrell, Licata & Tyrrell P.C.			
Address		66 East Main Street			
Address					
City	Marlton	State	NJ	ZIP	08053
Country	US	Telephone	856-810-1515	Fax	856-810-1454
ENCLOSED APPLICATION PARTS (check all that apply)					
<input checked="" type="checkbox"/> Specification		Number of Pages		9	
<input type="checkbox"/> Drawing(s)		Number of Sheets		<input type="checkbox"/> CD(s), Number	
<input type="checkbox"/> Application Data Sheet. See 37 CFR 1.76				<input checked="" type="checkbox"/> Other (specify) Return Postcard	
METHOD OF PAYMENT OF FILING FEES FOR THIS PROVISIONAL APPLICATION FOR PATENT (check one)					
<input checked="" type="checkbox"/> Applicant claims small entity status. See 37 CFR 1.27.				FILING FEE AMOUNT (\$)	
<input type="checkbox"/> A check or money order is enclosed to cover the filing fees					
<input checked="" type="checkbox"/> The Director is hereby authorized to charge filing fees or credit any overpayment to Deposit Account Number		50-1619		\$80.00	
<input checked="" type="checkbox"/> Payment by credit card. Form PTO-2038 is attached.					
The invention was made by an agency of the United States Government or under a contract with an agency of the United States Government.					
<input checked="" type="checkbox"/> No.					
<input type="checkbox"/> Yes, the name of the U.S. Government agency and the Government contract number are: _____					

Respectfully submitted,

SIGNATURE

Kathleen A. Tyrrell

TYPED or PRINTED NAME

Kathleen A. Tyrrell

TELEPHONE

856-810-1515

Date

11/4/03

REGISTRATION NO.

38,350

(if appropriate)

Docket Number:

DRE-0107

USE ONLY FOR FILING A PROVISIONAL APPLICATION FOR PATENT

This collection of information is required by 37 CFR 1.51. The information is used by the public to file (and by the PTO to process) a provisional application. Confidentiality is governed by 35 U.S.C. 122 and 37 CFR 1.14. This collection is estimated to take 8 hours to complete, including gathering, preparing, and submitting the complete provisional application to the PTO. Time will vary depending upon the individual case. Any comments on the amount of time you require to complete this form and/or suggestions for reducing this burden, should be sent to the Chief Information Officer, U.S. Patent and Trademark Office, U.S. Department of Commerce, P.O. Box 1450, Alexandria, VA 22313-1450. DO NOT SEND FEES OR COMPLETED FORMS TO THIS ADDRESS. SEND TO: Mail Stop Provisional Application, Commissioner for Patents, P.O. Box 1450, Alexandria, VA 22313-1450.

If you need assistance in completing the form, call 1-800-PTO-9199 and select option 2.

P19SMALL/REV05

DRE-0107


CERTIFICATE OF EXPRESS MAILING

"Express Mail" Label No. EL977714626US

Date of Deposit: November 4, 2003

I hereby certify that this paper is being deposited with the United States Postal Service "Express Mail Post Office to Addressee" service under 37 C.F.A. 1.10 on the date indicated above and is addressed to the Mail Stop Provisional Application, Commissioner for Patents, P.O. Box 1450, Alexandria, VA 22313-1450.

- 1) Patent Application Transmittal Letter (in duplicate);
- 2) Application consisting of 9 pages of specification, including 1 page of claims and 1 page of abstract;
- 3) USPTO Credit Card Payment Form authorizing payment in the amount of \$80.00 for filing fees;
- 4) Return Postcard.


Kathleen A. Tyrell

Electrospun Carbon Nanotube Reinforced Silk Fibers**Field of the Invention**

The present invention relates to synthetic fibrils
5 comprised of carbon nanotube and spider or silkworm silk and
methods for their production by electrospinning. These
fibrils exhibit enhanced strength and toughness as compared
to spider silk or silkworm silk alone and are useful
biomedically as surgical implants, sutures, tissue
10 engineering scaffolds and drug delivery agents. The
electroconductive properties of these fibrils renders them
useful as electrodes for brain/machine interfaces and neuron
regeneration as well. The strength and toughness of these
fibers also renders them useful in areas of blast and
15 ballistic protection.

Background of the Invention

In spite of the progress made over the past century in
polymeric fiber science and technologies, the search for a
20 truly strong and tough fiber continues. It is of practical
and scientific interest to explore the limit of strength and
toughness of fibrous materials; and to examine the factors
that contribute to the development of a combination of
strength and toughness in materials. There is an urgent need
25 for light weight fibrous materials that have high level of
combined strength and toughness in light of the increasing
need for higher level of ballistic protection for the
nation's security providers and warriors.

Strength and toughness are usually considered mutually
30 exclusive properties for materials.

In the world of natural fibers, spider silk has long
been recognized as the wonder fiber for its unique
combination of high strength and rupture elongation. Spider

silk has been shown to have a strength as high as 1.75 GPa at a breaking elongation of over 26% (Ko F. K. et al. Engineering properties of spider silk. Proceedings, MRS Annual Meeting, 2001). This gives rise to a toughness level
5 of two to three times of that of aramid and other industrial fibers.

The toughness property of fibers is an indication of the ability of a fiber to absorb impact energy. In a recent study on composite armors systems, it was shown, in terms of
10 the Florence model that the residual velocity of projectile is directly related to the toughness of the backing materials (Ko et al. MURI Final Report to US Army Research Office, DAAH 04-96-1-0018, 1997- 2002). Compared to the state of the art strong fibers, it was shown that spider
15 silk-backed armor provided the highest specific V_{50} or resistance to ballistic penetration.

As the threat for personnel armors is being expanded to include hand guns (9mm) and small arms (7.62mm) the demand for improvement of ballistic performance and areal densities
20 is greater. The ballistic limit of the armor system is expected to exceed 1000 m/s at an areal density of less than 3.5 lb/ft². At these threat levels, only the spider silk-based armor backing comes close to meeting the requirement. However, in spite of its exciting toughness characteristics,
25 spider silk remains a curiosity rather than a serious engineering materials. This is largely due to the lack of a practical method to harvest spider silk in quantity.

Recently, transgenic synthesis of spider silk polymer has made large scale manufacturing of spider silk possible
30 (Lazaris A. et al. Science 2002 295:472-476). In this process, recombinant spider silk, BIoSTEEL® in BELE® (Breed Early Lactate Early) goat system, was produced in combination with pronuclear microinjection and nuclear

transfer technologies resulting in a scalable manufacturing process for spider silk. While the biotechnology pathway to large scale manufacturing of spider silk is promising, the strength of the synthetic silk is far from satisfactory in spite of its high level of elongation at break.

Summary of the Invention

It has now been found that carbon nanotube is an ideal reinforcing material to strengthen synthetic spider silk and silkworm silk.

Accordingly, an object of the invention is to provide a synthetic fibril comprising carbon nanotube and spider silk or silkworm silk.

Another object of the present invention is to provide a method for producing strong and tough fibrils that comprises electrospinning carbon nanotube with spider silk or silkworm silk into single fibrils.

Detailed Description of the Invention

While recombinant techniques have made possible production of synthetic spider silk and silkworm silk in large quantities, these synthetic silks exhibit decreased strength. Carbon nanotube exhibits a Young's modulus of 1 TPa and a strength of 30-60 GPa at elongation at break ranging from 6-30%. Thus, carbon nanotube provides an ideal reinforcing material to strengthen synthetic spider silk and silkworm silk.

The present invention provides compositions and methods for producing stronger, tougher fibrils comprising spider silk or silkworm silk and carbon nanotube. In a preferred embodiment, to maximize the reinforcement effect of the carbon nanotube, fibrils of the present invention are prepared via an electrospinning process.

In the electrospinning process an electric field is generated between an oppositely charged polymer fluid and a fiber collection ground plate. A polymer solution is added to a glass syringe with a capillary tip. As the electrical potential is increased, the charged polymer solution is attracted to the screen. Once the voltage reaches a critical value, the charge overcomes the surface tension of the polymer cone formed on the capillary tip of the syringe and a jet of ultra fine fibers is produced. As the charged fibers are splayed, the solvent quickly evaporates and the solidified fibers are accumulated randomly on the surface of the collection screen. This results in a nonwoven mesh of nano to micron scale fibers. Varying charge density, polymer solution concentration and the duration of electrospinning can control fiber diameter and mesh thickness.

Experiments have been performed on electrospun fibrils of single walled carbon nanotube ranging from 1% to 5% by weight in a polyacrylonitrile (PAN) matrix (Adv. Mater. 2003 15(14):1161-1165). These fibrils are referred to herein as CNT/PAN composite fibrils.

In particular, the elastic properties of the CNT/PAN composite fibril were tested in an Atomic Force Microscope (AFM) using a tapping mode. The elastic moduli of the fibrils were evaluated based upon procedures such as described by Kracke and Damaschke (Appl. Phys. Lett. 2000 77:361-363). It was found that the Young's modulus of the CNT/PAN and PAN fibrils is a function of carbon nanotube volume fraction. Specifically, a 4.5 fold, increase in volume fraction effect by the introduction of less than 1.5% by volume of carbon nanotube to the PAN matrix.

Thus, it is believed that addition of carbon nanotube, with its superior strength and modulus characteristics, will

greatly enhance the strength of synthetic spider silk and silkworm silk.

Further, it is believed that the respective deformation characteristics of synthetic spider silk or silkworm silk and carbon nanotube are compatible. For example, it has been postulated that the most effective use of the tensile properties of two materials in a combined system is to have compatible elongation at break. The theory of elongation balance is well known in textile design (Ko, F.K., Krauland, K., and Scardino, F., "Weft Insertion Warp Knit for Hybrid Composites," Progress in Science and Engineering of Composites, eds. Hayashi et al., ICCM-V, Fourth International Conference on Composites, 1982, p. 982) and in composite analysis (ACK theory; Averston, J. Cooper, G., Kelly, A., In Properties of Fiber Composites. Conf. Proc. National Physical Laboratory, Guildford, UK:IPC. P.15). On the basis of elongation balance spider silk (20-30% elongation at break) and carbon nanotube (6-30% elongation at break) are among the most compatible material systems of known strong fibers. Thus, it is believed that a natural liquid crystalline polymer such as spider silk along with very small quantity of carbon nanotube, preferably in the range of about 1% to about 10% by weight, can be combined to produce light weight and high strength super fibrils by the electrospinning process.

To produce such fibrils, recombinant spider silk is obtained from commercial sources such as Nexia Biotechnologies. The carbon nanotube are then dispersed in the spider silk polymer solution. In a preferred embodiment, the spider silk solution comprises approximately 8% to about 20% by weight spider silk. In addition, the carbon nanotubes are preferably treated with a surfactant or a dispersion agent so that individual tubes are well

separated from each other, approaching the level of mono-dispersion. Such dispersion can be achieved by treating the carbon nanotube with a surfactant or dispersion agent to reduce the surface tension and then thoroughly mix the polymer/carbon nanotube system by sonication. Exemplary dispersion agents or surfactants for use in the present invention include, but are not limited to, polyvinyl pyrrolidone (PVP), polystyrene sulfonate (PSS), polyether, and protein. Once the carbon nanotube are dispersed the spinning dope is ready for electrospinning. The electrostatic charge along with the polymer flow helps in aligning the carbon nanotube in the spider silk polymer matrix.

It is believed that carbon nanotube can also be used to reinforce the strands of silk fibers of *Bombyx mori*, more commonly referred to as silkworm. Thus, the present invention is also applicable to silkworm silk.

Parameters for electrospinning including, but not limited to electric field strength, spinning distance and flow rate can be optimized to obtain the desired fiber diameter and concentration. Further, fibers of the present invention can be fabricated into linear assemblies, planar assemblies and/or three-dimensional assemblies as well as into the form of composite structures.

The structure and properties of the nanofiber composite fibrils can then be characterized at the nano/micro level and macro level. At the micro/nano level the surface and geometric properties of the spun composite fibrils are characterized by scanning electron microscopy (SEM), atomic force microscopy (AFM) and transmission electron microscopy (TEM). The mechanical properties of the fibrils are characterized by AFM and by micro-tensile tester

to determine the translation of the nano-materials to the bulk structures in yarn and nonwoven assemblies.

The spider or silkworm silk/carbon nanotube fibrils of the present invention are multifunctional materials having not only an unmatched level of combined strength and toughness but also having the function of controlled level of electrical conductivity. The spider or silkworm silk/carbon nanotube fibers are also biocompatible. Thus, the fibers of the present invention are useful in biomedical devices including, but not limited to surgical implants, sutures, tissue engineering scaffolds and drug delivery agents. The finess (nanoscale diameter) and the electrical conductivity also renders them useful as electrodes for brain/machine interfaces and numerous other applications including, but not limited to neuron regeneration. The strength and toughness of these fibers also renders them useful in areas of blast and ballistic protection, for example, in bulletproof vests, armor ceramic tile constrains and cargo explosion constrains.

What is Claimed is:

1. A synthetic fibril comprising carbon nanotube and spider silk or silkworm silk.

5 2. A method for producing the synthetic fibril of claim 1 comprising electrospinning carbon nanotube with spider silk or silkworm silk into single fibrils.

3. A biomedical device comprising the synthetic
10 fibril of claim 1.

4. A blast or ballistic protection device comprising the synthetic fibril of claim 1.

15 5. An electroconducting fiber comprising the fibril of claim 1.

ABSTRACT

Strong and tough synthetic fibrils of carbon nanotube and spider silk are provided. Methods for production of these synthetic fibrils and methods for their
5 use in biomedical devices, including those requiring electroconductivity, and areas of blast and ballistic protection are also provided.

Document made available under the Patent Cooperation Treaty (PCT)

International application number: PCT/US04/037076

International filing date: 04 November 2004 (04.11.2004)

Document type: Certified copy of priority document

Document details: Country/Office: US
Number: 60/517,128
Filing date: 04 November 2003 (04.11.2003)

Date of receipt at the International Bureau: 09 December 2004 (09.12.2004)

Remark: Priority document submitted or transmitted to the International Bureau in compliance with Rule 17.1(a) or (b)



World Intellectual Property Organization (WIPO) - Geneva, Switzerland
Organisation Mondiale de la Propriété Intellectuelle (OMPI) - Genève, Suisse

**This Page is Inserted by IFW Indexing and Scanning
Operations and is not part of the Official Record**

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☐ **BLACK BORDERS**
- ☐ **IMAGE CUT OFF AT TOP, BOTTOM OR SIDES**
- ☐ **FADED TEXT OR DRAWING**
- ☐ **BLURRED OR ILLEGIBLE TEXT OR DRAWING**
- ☐ **SKEWED/SLANTED IMAGES**
- ☐ **COLOR OR BLACK AND WHITE PHOTOGRAPHS**
- ☐ **GRAY SCALE DOCUMENTS**
- ☒ **LINES OR MARKS ON ORIGINAL DOCUMENT**
- ☒ **REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY**
- ☐ **OTHER: _____**

IMAGES ARE BEST AVAILABLE COPY.

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.